



1515623

Emisión: 02-2020 Rev 0

IN – EIC – F – 05 – REV1 – 07 DE JUNIO DE 2021

LUBRAL SUPER RACING PRO SAE 5W-20 API SN PLUS

SYNTHETIC MULTIGRADE OIL

DESCRIPTION

LUBRAL SUPER RACING PRO SAE 5W-20 API SN PLUS is a high-quality synthetic oil specially designed for modern engines. Made with synthetic bases and a state-of-the-art additive package that provides the engine with maximum protection against wear and oxidation, allowing to lengthen the drainage periods. Thanks to its anti-friction technology, it provides a long engineering life and contributes to fuel savings, as well as reducing CO2 emissions. Enhanced with carefully balanced chemistry that prevents LSPI damage in TGDI and GDI engines.

BENEFITS

- Protects modern TGDI and GDI engines against damage caused by LSPI (Low Speed Pre-Ignition).
- Protects engines that run on E-85 fuel.
- Fuel savings and reduction of harmful emissions into the atmosphere.
- Contains superior quality detergents and dispersants, preventing the accumulation of sludge and deposits in the engine.
- Synthetic technology that allows extended drain periods.
- Excellent fluidity at low temperatures facilitating starting in cold climates.
- Anti-friction technology that provides protection against metal-to-metal wear.

SPECIFICATIONS

- API SN Plus
- API SN
- ILSAC GF-5
- API Resource Conserving

APPLICATIONS

LUBRAL SUPER RACING PRO SAE 5W-20 API SN PLUS is recommended for gasoline engines in vehicles of the year 2020 and earlier with additional protection against preignition at low speeds. Consult your vehicle manual for the correct viscosity grade.

LUBRAL.com

LUBRAL SUPER RACING PRO SAE 5W-20 API SN PLUS

SYNTHETIC MULTIGRADE OIL

CHARACTERISTICS

TESTS	TEST METHOD	TYPICAL VALUE
SAE Grade	SAE J300	5W-20
Clasificación API		SN PLUS
Color	ASTM D1500	3.0
Density @20°C, g/mL	ASTM D4052	0.84
Kinematic Viscosity@ 40°C, cSt	ASTM D445	47
Kinematic Viscosity@ 100°C, cSt	ASTM D445	8.5
Viscosity index	ASTM D2270	160
Foaming formation tendency mL, max	ASTM D892	
Sequence 1		10/0
Sequence 2		50/0
Sequence 3		10/0
TBN	ASTM D2896	7.5
Cold start simulation, Cp @-30°C	ASTM D5293	5000
Flash point, °C	ASTM D92	230
Pour point, °C, max	ASTM D97	-42

Typical Characteristics are those obtained with normal tolerance of production and no constitute a specification. Variations that do not affect the yield product during the normal manufacturing and on different mixing locations are expected.

Information contained in this document is held to changes without previous advisement. The availability of the products could vary depending on the location. For further information, contact venta@lubral.com