

LUBRAL SUPER RACING PRO SAE 5W-30 API SN PLUS

SYNTHETIC MULTIGRADE OIL

DESCRIPTION

LUBRAL SUPER RACING PRO SAE 5W-30 API SN PLUS is a high-quality synthetic oil made with synthetic bases and a state-of-the-art additive package that provides the engine with maximum protection against wear and oxidation. Thanks to its technology, it provides long engineering life and contributes to fuel economy, as well as to lower CO2 emissions. Enhanced with carefully balanced chemistry that prevents damage caused by the LSPI phenomenon in TGDl and GDI engines. Meets API SN Plus and ILSAC (International Lubricant Standardization and Approval Committee) GF-5 requirements.

BENEFITS

- Protects modern TGDl and GDI engines against damage caused by LSPI (Low Speed Pre-Ignition).
- Saves fuel and reduces harmful emissions to the atmosphere.
- Protects engines operating on ethanol-containing fuel up to E85.

- Contains superior detergents and dispersants, preventing the accumulation of sludge and deposits in the engine.
- Synthetic technology that allows extended drain periods.
- Excellent fluidity at low temperatures, facilitating starting in cold climates.
- Anti-friction technology that provides protection against metal-to-metal wear.

SPECIFICATIONS

- API SN Plus
- API SN
- ILSAC GF-5
- API Resource Conserving

APPLICATIONS

LUBRAL SUPER RACING PRO SAE 5W-30 API SN PLUS is recommended for 2020 and earlier vehicles with additional protection against pre-ignition at low speeds.

Consult your vehicle manual for the correct viscosity grade.

LUBRAL SUPER RACING PRO SAE 5W-30 API SN PLUS

SYNTHETIC MULTIGRADE OIL

CHARACTERISTICS

TESTS	TEST METHOD	TYPICAL VALUE
SAE Grade		5W-30
Clasificación API		SN PLUS
Color	ASTM D1500	2.0
Appearance	Visual	Bright
Density @20°C, g/mL	ASTM D4052	0.84
Kinematic Viscosity@ 40°C, cSt	ASTM D445	60
Kinematic Viscosity@ 100°C, cSt	ASTM D445	10
Viscosity index	ASTM D2270	160
Foaming formation tendency mL, máx	ASTM D892	
Sequence 1		10/0
Sequence 2		50/0
Sequence 3		10/0
TBN	ASTM D2896	7.5
Cold start simulation, Cp @-30°C	ASTM D5293	5000
Flash point, °C	ASTM D92	232
Pour point, °C	ASTM D97	-39

Typical Characteristics are those obtained with normal tolerance of production and no constitute a specification. Variations that do not affect the yield product during the normal manufacturing and on different mixing locations are expected.

Information contained in this document is held to changes without previous advisement. The availability of the products could vary depending on the location. For further information, contact venta@lubral.com