

# **LUBRAL WORM GEAR 220**

**GEAR OIL** 

## **DESCRIPTION**

Extreme pressure lubricant for screw-type gears formulated with mineral oils and additives with high technology that gives it high performance against oxidation and corrosion, also guarantees the formation of a metal-metal film, protecting the life of the gears. It presents high resistance to mechanical shear, even in systems with high load without loss in viscosity.

#### **BENEFITS**

- Excellent anti-wear property
- · Does not attack yellow metals
- · Resistance to foaming
- · Resistant to oxidation

### **APPLICATIONS**

Due to the additives used, their use is recommended in ferrous and non-ferrous metals. Useful in metal forming and removal applications

#### **CHARACTERISTICS**

| TESTS                           | TEST METHOD | TYPICAL<br>VALUE |
|---------------------------------|-------------|------------------|
| ISO Viscosity Grade             |             | 220              |
| Appearence                      | Visual      | Brilliant        |
| Color                           | ASTM D1500  | 3                |
| Density @15°C, g/ml             | ASTM D1298  | 0.88             |
| Kineamtic Viacosity @100°C, cSt | ASTM D445   | 19               |
| Kinematic Visosity @40°C, cSt   | ASTM D445   | 220              |
| Viscosity Index                 | ASTM D2270  | 95               |
| Flash Point, °C                 | ASTM D92    | 220              |
| Resistence To Rust Formation    | ASTM D665   | Pass             |
| Pour Point, °C                  | ASTM D97    | -6               |
| Copper Corrosion                | ASTM D130   | 1a               |
| Foaming, ml/min, máx.           |             |                  |
| Sequence I                      | ASTM D892   | 20/0             |
| Seuqnce II                      | D892        | 50/0             |
| Seugnce III                     | D892        | 20/0             |

Typical Properties are those obtained with normal production tolerance and do not constitute a specification. Variations that do not affect product performance are expected during normal manufacturing and at different mixing locations.

The information in this document is subject to change without notice. Product availability may vary depending on the location. For more information, you can contact us at venta@lubral.com

